

APPLICATION
FOR
UNITED STATES LETTERS PATENT

TITLE: EXHAUST GAS PURIFYING CATALYST
APPLICANT: TATSUYA YOSHIKAWA

CERTIFICATE OF MAILING BY EXPRESS MAIL

Express Mail Label No. EL298426833US

I hereby certify under 37 CFR §1.10 that this correspondence is being deposited with the United States Postal Service as Express Mail Post Office to Addressee with sufficient postage on the date indicated below and is addressed to the Commissioner for Patents, Washington, D.C. 20231.

June 22, 2001

Date of Deposit

Signature

Samantha Bell
Typed or Printed Name of Person Signing Certificate

EXHAUST GAS PURIFYING CATALYST

BACKGROUND OF THE INVENTION

5 Field of the Invention:

10 This invention relates to a catalyst for purifying exhaust gases emitted from an internal combustion engine or a boiler and a method for purifying the exhaust gas by the use of this catalyst. More specifically, it relates to an exhaust gas purifying catalyst capable of removing in high efficiency nitrogen oxides (NO_x) in the lean atmosphere containing moisture and a method for purifying the NO_x by the use of this catalyst.

Description of Related Art:

15 The NO_x emitted from internal combustion engines is a causal substance for acid precipitation and photochemical smog. In recent years, developing a means for decreasing NO_x emission has been desired by the social consensus voiced about the environmental preservation. Though the purification or decomposition of NO_x under an oxygen-excess atmosphere by catalytic method has been energetically studied since a long time ago, it has not been easy to discover an effective technique.

20 Titania-carried vanadium catalysts using ammonia as a reducing agent have been established as the technique for purifying NO_x . It has been already put to practical use such as in large stationary sources for generation, but the effort to mount the systems has not yet been realized in mobile sources such as diesel cars on account of issues like slipping of
25 unreacted ammonia.
30

In the circumstance, it was found to be effective for NO_x purification to apply copper ion-exchanged zeolite using

hydrocarbon as a reducing agent. With this discovery, zeolite based catalyst systems have been proposed in JP-A-63-100919 and JP-A-4-363146.

5 SUMMARY OF THE INVENTION

These catalysts, however, have entailed problems such as being still low selectivity at steady state or readily incurring deterioration under the influence of moisture.

This invention has been done in view of the affairs
10 mentioned above and provides a catalyst capable of purifying, with high efficiency, NO_x contained in the lean atmosphere in the presence of a hydrocarbon, and a method for the purification of NO_x in exhaust gases by the use of the catalyst.

The object is accomplished by a catalyst with the
15 composition formed by an intimate contact of zeolite and an oxide made from the complex of zirconium and manganese and/or cobalt in particularly like physical mixing.

The object is further accomplished by a method for the purification of NO_x in exhaust gases by the use of the catalyst.

According to this invention, it is possible to provide
20 a catalyst with the composition formed by an intimate contact of zeolite and an oxide made from the complex of zirconium and manganese and/or cobalt in particularly like physical mixing and that is capable of efficiently removing NO_x in an
25 oxygen-excess atmosphere containing moisture.

The above and other objects, features and advantages of the present invention will become clear from the following description of the preferred embodiments.

30 DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

We have pursued a diligent study with a view to solving the problem mentioned above, and found that a composition

obtained by physically mixing a composite oxide containing zirconium and manganese and/or cobalt (a first component) and zeolite (a second component) has a specifically high performance as a NO_x purifying catalyst in a lean atmosphere when it is applied with reducing agents such as hydrocarbon. This invention has been achieved.

Specifically, the first component alone or the second component alone does not purify NO_x (less than 15% at normal operating conditions), but the first and second components, when contacted closely to each other like a method of physical mixing, prominently reveal the catalytic function of reducing NO_x under oxygen-excess atmosphere. When the active component of the catalyst is applied to a monolithic carrier, which is generally used in an automobile catalyst, it is commendable for this active component to be applied in a homogenous physical mixture so as to manifest the performance to the greatest possible extent. When the individual components of the catalyst are applied as different layers, the catalyst is still effective. Though the detail of the reaction is not known, it may say that the two components of the catalyst work synergetically for NO_x reduction. For example, the first component may work for the oxidation of NO and hydrocarbon, and the second component may work for the activation of hydrocarbon and NO₂. The catalytic activity is high at steady state when compared with Cu-ZSM5 as later shown in examples (temperature decrease test). Therefore the present invention is different from the system already found zeolite-based catalyst like Cu-ZSM5, Mn-ZSM5 and so on.

The first component is not particularly restricted but only required to be a composite oxide containing zirconium and manganese and/or cobalt. The composite oxide, when analyzed by the X-ray diffraction, shows a discernible peak

of ZrO_2 and does not show a discernible peak solely of oxides of Mn or Co. Thus, the first component is to be understood that Mn and/or Co is essentially complexed with ZrO_2 .

5 The weight ratio of manganese and/or cobalt to zirconium is not restricted but only required to be enough for the produced catalyst to acquire an ability to reduce NO_x . The weight ratio of each of the oxides may comprise from 1 to 50 weight parts, preferably from 5 to 40 weight parts, per 100 weight parts of zirconium oxide. If this ratio drops below
10 1 weight part, the shortage will be at a disadvantage in preventing a satisfactory ability to reduce NO_x . Conversely, if the ratio exceeds 50 weight parts, the excess will be at a disadvantage in bringing the ability to reduce NO_x proportionately thereto. Instead of zirconium oxide,
15 complex oxides containing zirconium oxide such as a cerium-zirconium oxide, which is widely applied as the three-way catalyst component, and manganese and/or cobalt may be cited.

20 The method for preparing the composite oxide containing zirconium and manganese and/or cobalt is not restricted. The preparation may be effected by any methods well known to an ordinary skill in the art, such as a co-precipitation, a sol-gel, or an impregnation method. In the impregnation method, for example, the preparation is attained by impregnating powdered
25 zirconium oxide with a solution of the raw material salt such as a nitrate, an acetate, or an oxalate of manganese and/or cobalt, drying the impregnated powder at a temperature of $100^\circ C$ to $250^\circ C$, and then calcining the dried powder at a temperature of $300^\circ C$ to $800^\circ C$, preferably of $400^\circ C$ to $700^\circ C$.
30 The atmosphere during the calcinations is not restricted, but air may be cited. Though the kind of zirconium oxide to be used at this time is not particularly discriminated, the

surface area of the zirconium oxide (as determined by the BET method) may comprise not less than 5 m²/g, preferably not less than 20 m²/g, and especially in the range of 20 to 200 m²/g.

5 The first component may be deposited on a refractory inorganic substance such as silicon carbide, alumina, titania, or silica. This deposition is attained by impregnating the substance in a powdery state with the solution of a raw material salt such as a nitrate, acetate, or oxalate of zirconium and
10 manganese and/or cobalt, drying the impregnated powder, and calcining the dried powder.

Further, the first component may incorporate therein some other element, for example, as an oxide, such as at least one element selected from the group consisting of bismuth,
15 iron, cerium, praseodymium, gadolinium, lanthanum, barium, strontium, calcium, potassium, cesium, and yttrium. Commendably, the amount of such an element may comprise from 0.2 to 50 weight percent, preferably from 1 to 40 weight percent, based on the weight of manganese and/or cobalt (weight as
20 metal). By having this element participate in the complex, it is possible to increase the efficiency of NO_x purification and to improve the produced catalyst in thermal stability.

The second component is a family of zeolite, not restricted, but may include ZSM-5, Ferrierite, Faujasite,
25 β-zeolite, and Mordenite. These are usually crystalline aluminosilicate

The zeolite is a material that has specific pore structure and solid acid property. It has been suggested that for this invention, this quality of the material is indispensable for
30 purifying NO_x. To be specific, the zeolite having proper pore structure and acid strength and/or amount is essential for the catalyst of this invention.

09888009 "052201

The acid amount of the zeolite is generally expressed by the atomic ratio of Si and Al, which are components of the zeolite. For a fixed structure, it is said that in proportion as the content of Al thereof increases the acid amount of the zeolite increases. For the zeolite to be used in this invention, it is essential to have a proper amount of acidity. The Si/Al ratio of this zeolite is properly in the range of 1 to 150: 1, preferably in the range of 5 to 80: 1. Among other conceivable types of zeolite, the proton type zeolite proves particularly advantageous. It may be partly modified with iron, cerium, lanthanum, phosphorus, boron, gallium, magnesium, calcium and mixtures thereof or preferably with cerium, lanthanum, phosphorus, boron or mixtures thereof. The term "modification" as used herein means the introduction of a new element by a method such as ion exchange, impregnation, or exchange of skeleton Al ion. This modification is possible to alter the acid characteristics of the zeolite and improve the heat resistant property and durability. The zeolite may also be modified with the following component, namely copper, cobalt and manganese up to 0.5 weight percent, preferably up to 0.3 weight percent, based on the weight of the zeolite. This is for the modification of zeolite to remove residues such as carbon deposited in the zeolite pores during use. If the content exceeds the above-defined value, the catalyst behaves for the reaction like the Cu-zeolite catalyst, namely exhibits low selectivity at steady state condition, which is shown below in Referential Example 1 as a conversion of the temperature decrease test.

Since the pore structure is specified by the basic structure and skeleton of the zeolite and effects the interaction with a hydrocarbon, the zeolite preferably has

00000000 "062201

Though the composition resulting from the physical mixture of the first and second components may be used in its unmodified form, it is preferably used in the form of a coat formed on a refractory three-dimensional structure in the case of purifying exhaust gases from a motorcar. Examples of the structure may include pellets and a monolithic carrier. The monolithic carrier is preferred over the pellets in respect of the smallness of the pressure loss. As the monolithic carrier, what is generally called a honeycomb carrier can be used. Particularly, the honeycomb carriers using cordierite, mullite, α -alumina, zirconia, titania, titanium phosphate, aluminum titanate, sponduemene, aluminosilicate, and magnesium silicate as materials prove advantageous. Among other honeycomb carriers, those made of cordierite prove particularly favorable. Besides, integral structures using oxidation proof heat resistant metals such as stainless steel and Fe-Cr-Al alloys may be usable.

Such a monolithic carrier is produced by an extrusion molding method or a method that consists in tightly reeling a sheet like element into a roll, for example. The openings in the carrier for passing the gas (cells) may be shaped like a hexagon, a tetragon, a triangle, or a corrugation, whichever fits the occasion best. The cell density (number of cells per cross section of 6.45 cm^2) is not particularly restricted but may be cited in the range of 100 to 1200 cells, preferably in the range of 200 to 600 cells, in view of the coatability of slurry and the durability of coat.

In this invention, the method for depositing the composition resulting from physical mixture of the first and second components on the structure is not particularly discriminated. An ordinary impregnation method can be used. To be specific, this impregnation is attained by immersing

the structure in a slurry obtained by physically mixing the first and second components, straining the impregnated structure to expel excess slurry, then drying the wet structure at a temperature of 80°C to 250°C, preferably of 100°C to 150°C, and optionally calcining the dried structure at a temperature of 300°C to 800°C, preferably of 400°C to 600°C, for a period of 0.5 to 3 hours, preferably of 1 to 2 hours.

The amount of the composition to be deposited on the structure is not particularly restricted, but generally in the range of 100 to 400 g, preferably 150 to 300 g, per liter of the structure. If this amount drops below 100 g, the shortage will be at a disadvantage in lowering NO_x reducing capacity. Conversely, if the amount exceeds 400 g, the excess will be at a disadvantage in imparting increased resistance to the cells and aggravating the pressure loss during use.

One of the features of the invention is that the catalyst exhibits similar activity in the programmed temperature decrease test, as set forth below, as in the programmed temperature increase test, thereby exhibiting high NO_x conversions constantly. Another feature of the invention is that the catalyst has ability for adsorbing and/or storing NO_x in low temperatures, thereby providing a catalyst system using this catalyst.

The catalyst obtained as described above can purify NO_x by utilizing, as a reducing agent, the hydrocarbon such as propylene, methane, propane, lamp oil, light oil, heavy oil contained in the atmosphere; the unburnt fuel of an internal combustion engine such as a gasoline or diesel engine; or ammonia. Particularly, it can efficiently purify the NO_x that is contained in the gas entraining excess oxygen and moisture. When the amount of the reducing agent is not sufficient and the NO_x is not reduced sufficiently, a reducing agent mentioned

above may be properly added from the exterior of system. The term "excess oxygen" as used herein means that the amount of oxygen contained in the gas is larger than the amount of oxygen sufficient for oxidizing the components. To be specific, it means that the oxygen is contained usually in an amount of 1 of 20 vol. %, based on the volume of the exhaust gas. The expression that the moisture is contained means the atmosphere that contains moisture in the approximate range of 3 to 15%, based on the volume of the exhaust gas.

As exemplified as set forth below, the catalyst of the present invention can be used for the purification of NO_x in the range of 200°C to 600°C , preferably 250°C to 500°C .

Examples of the gas to be treated may include NO_x -containing exhaust gases emitted from the internal combustion engine using gasoline as the fuel and emitted from the internal combustion engine using light oil or LPG as the fuel. The catalyst manifests an excellent NO_x purifying capacity, particularly in the atmosphere of a large air-fuel ratio (lean), which is held to permit purification only with difficulty, the air-fuel ratio (A/F) being so large as to be not less than 15.

EXAMPLES

Now, this invention will be described more specifically below with examples. It should be noted, however, that this invention is not limited by these examples.

The zeolite used in Examples is of proton type unless otherwise stated.

EXAMPLE 1

One thousand (1000) g of zirconium oxide was impregnated with an aqueous solution containing a 100 g equivalent of

manganese nitrate as manganese oxide (MnO_2), dried overnight at 120°C , and calcined at 550°C for one hour. The resultant manganese-deposited zirconium oxide and ZSM-5 ($\text{Si}/\text{Al} = 27$, available from Zeolyst International) were separately ball
5 milled in an aqueous solution, and mixed at a weight ratio (solid ratio) of 2: 8. The produced mixture was applied to a monolith made of cordierite (400 cells, 0.043 liter, available from NGK Insulators, LTD in Japan) so as to account for an amount of 180 g/L. The coated monolith thus obtained
10 was dried at 120°C and then calcined at 500°C for one hour to obtain a catalyst.

In the reaction gas shown in Table 1, the produced catalyst was heated from 100°C to 550°C at an increasing rate of $20^\circ\text{C}/\text{min}$. and cooled from 550°C to 150°C at a decreasing rate of $20^\circ\text{C}/\text{min}$.
15 to determine conversion efficiencies of NO_x . The results are shown in Table 2 below.

TABLE 1. CONDITIONS OF REACTION GAS

Conditions for rating model gas
NO: 400 ppm, Propylene (n-decane only in Example 6): 1800 ppm Cl (normalized to carbon concentration), CO: 400 ppm, O_2 : 8.5 vol %, Water: 10 vol % Total flow volume: 28 L/min., SV: About 40,000 h^{-1}

NO was analyzed with a chemical emission spectral
20 analyzer (CLD), and the hydrocarbon with a hydrogen flame ionizing analyzer (NDIR), respectively.

COMPARATIVE EXAMPLE 1

A catalyst was prepared according to the procedure of
25 Example 1 while using γ -alumina instead of the zirconium

oxide.

COMPARATIVE EXAMPLE 2

A catalyst was prepared according to the procedure of
5 Example 1 while using silica-alumina of Si/Al = 0.2 instead
of the ZSM-5.

COMPARATIVE EXAMPLE 3

A catalyst was prepared according to the procedure of
10 Example 1 while using silicalite (Si/Al = 300) instead of
the ZSM-5.

EXAMPLE 2

A catalyst was prepared according to the procedure of
15 Example 1 while adding a 40 g equivalent of cerium nitrate
as cerium oxide (CeO_2) besides the manganese nitrate.

EXAMPLE 3

A catalyst was prepared according to the procedure of
20 Example 2 while using mordenite (Si/Al = 10, available from
Zeolyst International) instead of the ZSM-5.

EXAMPLE 4

A catalyst was prepared according to the procedure of
25 Example 1 while using cobalt nitrate instead of the manganese
nitrate.

EXAMPLE 5

An aqueous solution of a 15% equivalent of manganese
30 nitrate as manganese oxide (MnO_2) and an aqueous solution of
a 15% equivalent of zirconium oxynitrate as zirconium oxide
(ZrO_2) were added to a commercially available alumina (150

a coat of 200g per liter of catalyst, in which 180 g was based on the weight of Cu-ZSM-5 material and 20 g based on the weight of silica.

The catalysts obtained in the examples cited above were tested for performance by the method described in Example 1. The results are shown in Table 2.

TABLE 2

	Programmed temperature increase		Programmed temperature decrease	
	Tmax(°C)	NOx Conv. (%)	Tmax(°C)	NOx Conv. (%)
Ex. 1	370	50	300	55
Com. Ex. 1	460	15	410	20
Com. Ex. 2	360	10	320	15
Com. Ex. 3	380	20	300	15
Ex. 2	380	70	280	75
Ex. 3	330	80	290	85
Ex. 4	390	60	230	45
Ex. 5	390	50	300	50
Ex. 6	380	85	290	88
1*	420	60	450	30
Ex. 9	365	45	295	50

Tmax: Catalyst inlet temperature at which the conversion efficiency of NO_x reached the maximum.

NO_x Conv: The conversion efficiency of NO_x at Tmax.

1*: REFERENTIAL EXAMPLE 1

EXAMPLE 7

The catalyst prepared in Example 3 was left standing

at 700°C for 50 hours in a reaction gas of the conditions shown in Table 1 to determine the durability under the influence of the standing. The results are shown in Table 3.

EXAMPLE 8

A catalyst was prepared according to the procedure of Example 7 while using, during the preparation of the catalyst, what was obtained by impregnating mordenite (Si/Al = 10, available from Zeolyst International) with 0.3 weight % each of magnesium, phosphorus, and cerium. The catalyst was tested for durability by the procedure described in Example 7 and then tested for performance by the procedure described in Example 1. The results are shown in Table 3.

TABLE 3 (Durability)

	Programmed temperature increase		Programmed temperature decrease	
	Tmax(°C)	NOx Conv.(%)	Tmax(°C)	NOx Conv.(%)
Ex. 7	350	70	300	75
Ex. 8	330	80	290	85

Tmax: Catalyst inlet temperature at which the conversion efficiency of NO_x reached the maximum.

NO_x Conv: The conversion efficiency of NO_x at Tmax.

EXAMPLE 9

ZSM-5 powder was ball milled in an aqueous solution and then applied to a monolith carrier (supra) to account for a ratio of 144 g/L. The resulting ZSM-5 coated monolith was dried and then calcined at 500°C for one hour.

The manganese-deposited zirconia powder, prepared according to the procedure of Example 1, was ball milled and

then applied to the calcined monolith to account for a ratio of 36 g/L. The resulting monolith was dried and calcined at 500°C for one hour. The total amount of the coated materials was 180 g/L with the second coat/ the first coat being 2/8.

5 The test result is shown in Table 2 above.

10 The catalysts of this invention excel not only in the fresh state but also in the state assumed after the standing (Examples 7 and 8), in terms of the conversion of NO_x at T_{max} in the programs of temperature increase and temperature decrease, compared with the fresh catalysts obtained in the comparative examples (Comparative Examples 1 to 3).

15 The entire disclosure of Japanese Patent Application No. 2000-195143 filed on June 28, 2000 including specification, claims and summary are incorporated herein by reference in its entirety.

09888009.062201